

BINDER 2K POLIURETANICO SEMILUCIDO

Code	Binder	% by weight: Pigment/Binder
KJL.1408	KJL.1408	30 / 70

Description

2K Polyurethane Semi Gloss Enamel. Excellent coverage and fast drying with exceptional chemical-physical properties.
 Realisable by mixing pigment and binder in the right mixing ratio.

Recommended for

Particularly suitable for all Industrial and Agricultural machinery.

Specific Weight Kg/Lt

1,4-1,5

VOC (g/Lt) product ready to use Dir. 2004/42/CE

IIA(j) (500)500

°Gloss

50-65

Application T°C

10-45

Pot-Life 20°C


2-3 H

Colour Code

TUTTI I COLORI

Application

SPRAY



Use graduated stick N.: 2

		10-25°C	25-35°C	35 - 45 °C	By Vol.	By Weight	Vol. x Airles
	Product	KJL.1408	KJL.1408	KJL.1408		100	
	Hardener	FK9.7777	FK9.6666	FK9.6663	5+1	20	
	Hardener	FK9.0006	FK9.0006	FK9.0006		25	
	Thinner	RDL.P333	RDL.P333	RDL.P333		10	
	Viscosity (sF 4 20°C)					17-18	


BINDER 2K POLIURETANICO SEMILUCIDO

Code

KJL.1408




Nozzle (mm)
Pression (bar)
N. of Passes



Flash off (min) at 20°C
Dust off (min) at 20°C



Drying Time at 20°C (h)
Drying Time at 60°C (h)
Drying Short IR (min x cm)



Dry microns per pass
Micron secchi (min \ max)
Theoretical yield (mq\lt) x 50



Conventional

Gravity Feed

Suction Feed Spray

HVLP

Airless

1,3-1,4

1,4-1,6

1,3-1,4

1140/1350

3-4

4

0,7

48-144

2-3

2-3

2

1+1

5-10

5-10

5-10

5-10

15-20

15-20

15-20

15-20

20-24

20-24

20-24

20-24

1

1

1

1

25'X40

25'X40

25'X40

25'X40

25-30

25-30

25-30

20-25

50-75

50-75

50-75

7-8

7-8

7-8

Sanding with Orbital



Polishing



Overpaintable with...

Max Time to overcoat at 20°C

Min Time to overpaint in 20°C



Store free from frost



Store in cool place



Protect from umidity



Use fresh air mask