

BINDER NITROCOAT

Code	Binder	% by weight: Pigment/Binder
KJN.1755	KJN.1755	10 / 90

Description

1K Nitrocellulose Synthetic Semiglossy Enamel. Fast drying and high brilliance. Good elasticity and strong resistance to light.
 Realisable by mixing pigment and binder in the right mixing ratio.

Recommended for

Suitable for all Industrial structures(manufacturing machines, lifts and small agricultural machineries...)

Specific Weight Kg/Lt

1

VOC (g/Lt) product ready to use Dir. 2004/42/CE

IIA(I) (500)500

°Gloss

60-70

Application T°C

10-45

Pot-Life 20°C


N.A.

Colour Code

TUTTI I COLORI

Application

SPRAY



Use graduated stick N.:

		10-25°C	25-35°C		By Vol.	By Weight	Vol. x Airles
	Product	KJN.1755	KJN.1755		2	100	3
	Hardener						
	Hardener						
	Thinner	RDL.P333	RDL.P333		1	50	1
	Viscosity (sF 4 20°C)				19	19	30


BINDER NITROCOAT

Code

KJN.1755




Nozzle (mm)
Pression (bar)
N. of Passes



Flash off (min) at 20°C
Dust off (min) at 20°C



Drying Time at 20°C (h)
Drying Time at 60°C (h)
Drying Short IR (min x cm)



Dry microns per pass
Micron secchi (min \ max)
Theoretical yield (mq\lt) x 50



Conventional

Gravity Feed

Suction Feed Spray

HVLP

Airless

1,3-1,4

1,4-1,6

1,3-1,4

1140/1350

3-4

4

0,7

48-144

2-3

2-3

2-3

1+1

5

5

5

10

5

5

5

10

2-3

2-3

8-10

8-10

20'

20'

20'

20'

20-25

20-25

20-25

30-35

50-60

50-60

8-9

8-9

8-9

Sanding with Orbital



Polishing



Overpaintable with...

Max Time to overcoat at 20°C
Min Time to overpaint in 20°C



Store free from frost



Store in cool place



Protect from umidity



Use fresh air mask